



ISO 9001:2008 Registered

Material: Nomex Blend[®]

MATERIAL	CONTENT	CONSTRUCTION	WEIGHT	COLOR(s)
Nomex Blend [®]	20% Nomex [®] / 80% Lenzing FR [®]	1 x 1 Circular Knit	Approx. 7.0 oz. / sq. yd. (+1.0/-0.5)	White (Standard), also Red, Orange, Navy Blue, Charcoal Grey, and Black

TEST RESULTS FROM UNDERWRITERS LABORATORIES

	NOMEX BLEND [®] TEST RESULT	NFPA 1971 REQUIREMENT
TPP (THERMAL PROTECTIVE PERFORMANCE)	34.9	Minimum 20
MATERIAL BURST STRENGTH	364 N (82.5 lbf)	Minimum: 225 N (51 lbf)
CLEANING SHRINKAGE	within tolerance	Maximum 5 % (+ or -)
SEAM BREAKING STRENGTH	542.5 N (123 lbf)	Minimum: 181 N (41 lbf)
+ = Grows - = Shrinks		

CERTIFICATIONS

Nomex Blend material: ATPV = 10.1 cal/cm² - HRC 2 (double ply material) – in accordance with ASTM International Standard Test Method F1959-1999.

CLEANING AND STORAGE

Hoods maintain protective properties after machine washing.

- Machine wash only using regular detergent
- Water temperature not to exceed 130° F
- Do not use chlorine bleach or detergents containing chlorine
- Do not use fabric softeners or detergents containing fabric softeners
- Do not wring hood to dry. Squeeze hood to remove excess water.
- Shape and lay flat in a dry, cool, shaded location to dry.
- Or Tumble dry, low heat.
- Do not commercially dry clean.
- Do not store your hood in direct sunlight.

NFPA 70E PERFORMANCE SPECIFICATIONS OF ASTM F 1959/F 1959M-05a:

*Level 1 = minimum 5 cal/cm² to 7 cal/cm²
 Level 2 = minimum 8 cal/cm² to 24 cal/cm²
 Level 3 = minimum 25 cal/cm² to 39 cal/cm²
 Level 4 = minimum 40 cal/cm² and over*

All weights and measurements are approximate

P.O. Box 248 • Lehighton, PA • 18235

Phone: 610-377-6273 • Fax: 610-377-6221

E-mail: cs@majesticfireapparel.com • Website: www.majesticfireapparel.com