



ISO 9001:2008 Registered

## Material: PBI<sup>®</sup>

MATERIAL	CONTENT	CONSTRUCTION	WEIGHT	COLOR(s)
P.B.I. <sup>®</sup>	20% P.B.I. <sup>®</sup> / 80% Lenzing FR <sup>®</sup>	1 x 1 Circular Knit	Approx. 6.0 oz. / sq. yd. (+1.0/- .5)	Lt. Brown

### TEST RESULTS FROM UNDERWRITERS LABORATORIES

	P.B.I. <sup>®</sup> TEST RESULT	NFPA 1971 REQUIREMENT
TPP (THERMAL PROTECTIVE PERFORMANCE)	39.3	Minimum 20
MATERIAL BURST STRENGTH	311.8 N (70.7 lbf)	Minimum: 225 N (51 lbf)
CLEANING SHRINKAGE	within tolerance	Maximum: 5 % (+ or -)
SEAM BREAKING STRENGTH	571 N (129.4 lbf)	Minimum: 181 N (41 lbf)
+ = Grows    ~ = Shrinks		

#### CLEANING AND STORAGE

Hoods maintain protective properties after machine washing.

- Machine wash only using regular detergent
- Water temperature not to exceed 130° F
- Do not use chlorine bleach or detergents containing chlorine
- Do not use fabric softeners or detergents containing fabric softeners
- Do not wring hood to dry. Squeeze hood to remove excess water.
- Shape and lay flat in a dry, cool, shaded location to dry.
- Or Tumble dry, low heat.
- Do not commercially dry clean.
- Do not store your hood in direct sunlight.

*All weights and measurements are approximate*

P.O. Box 248 • Lehighton, PA • 18235

Phone: 610-377-6273 • Fax: 610-377-6221

Email: [cs@majesticfireapparel.com](mailto:cs@majesticfireapparel.com) • Website: [www.majesticfireapparel.com](http://www.majesticfireapparel.com)