



ISO 9001:2008 Registered

Material: P.B.I. Gold[®]

MATERIAL	CONTENT	CONSTRUCTION	WEIGHT	COLOR(s)
P.B.I. Gold [®]	40% P.B.I. [®] / 60% Kevlar	1 x 1 Circular Knit	Approx. 8.0 oz. / sq. yd. (+1.0/-0.5)	Mustard Yellow (Standard) or Black

TEST RESULTS FROM UNDERWRITERS LABORATORIES

	P.B.I. GOLD [®] TEST RESULT (test results with PBI inner layer)	NFPA 1971 REQUIREMENT
TPP (THERMAL PROTECTIVE PERFORMANCE)	31.1	Minimum 20
MATERIAL BURST STRENGTH	580.1 N (131.5 lbf)	Minimum: 225 N (51 lbf)
CLEANING SHRINKAGE	within tolerance	Maximum 5 % (+ or -)
SEAM BREAKING STRENGTH	771.6 N (174.9 lbf)	Minimum: 181 N (41 lbf)
+ = Grows - = Shrinks		

CLEANING AND STORAGE

Hoods maintain protective properties after machine washing.

- Machine wash only using regular detergent
- Water temperature not to exceed 130° F
- Do not use chlorine bleach or detergents containing chlorine
- Do not use fabric softeners or detergents containing fabric softeners
- Do not wring hood to dry. Squeeze hood to remove excess water.
- Shape and lay flat in a dry, cool, shaded location to dry.
- Or Tumble dry, low heat.
- Do not commercially dry clean.
- Do not store your hood in direct sunlight.

All weights and measurements are approximate.

P.O. Box 248 • Lehighton, PA • 18235
 Phone: 610-377-6273 • Fax: 610-377-6221
 EMAIL: cs@majesticfireapparel.com • WEBSITE: www.majesticfireapparel.com